

		SI	CGS
Remanence	Br	1.25-1.30 T	12.5-13.0 kG
Coercivity	Hcb	≥ 955 kA/m	≥ 12.0 kOe
Intrinsic Coercivity	Hcj	≥ 2786 kA/m	≥ 35.0 kOe
Maximum Energy Product	(BH) max	302-334 kJ/m ³	38-42 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.44 %/c	-0.40 %/c

