

G43EH



		SI	CGS
Remanence	Br	1.29-1.34 T	12.9-13.4 kG
Coercivity	Hcb	≥ 971 kA/m	≥ 12.2 kOe
Intrinsic Coercivity	Hcj	≥ 2388 kA/m	≥ 30.0 kOe
Maximum Energy Product	(BH) max	318-350 kJ/m ³	40-44 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.47 %/c	-0.44 %/c

