

# G47UH



		SI	CGS
Remanence	Br	1.35-1.40 T	13.5-14.0 kG
Coercivity	Hcb	≥ 1011 kA/m	≥ 12.7 kOe
Intrinsic Coercivity	Hcj	≥ 1990 kA/m	≥ 25.0 kOe
Maximum Energy Product	(BH) max	350-382 kJ/m <sup>3</sup>	44-48 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	$\partial$	-0.10 %/c	-0.11 %/c
Temperature Coefficient of Hcj	$\beta$	-0.57 %/c	-0.51 %/c

