

# G51SH



		SI	CGS
Remanence	Br	1.41-1.46 T	14.1-14.6 kG
Coercivity	Hcb	≥ 1051 kA/m	≥ 13.2 kOe
Intrinsic Coercivity	Hcj	≥ 1592 kA/m	≥ 20.0 kOe
Maximum Energy Product	(BH) max	382-414 kJ/m <sup>3</sup>	48-52 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	$\partial$	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	$\beta$	-0.61 %/c	-0.55 %/c

