

# N35EHS



		SI	CGS
Remanence	Br	1.16-1.23 T	11.6-12.3 kG
Coercivity	Hcb	≥ 876 kA/m	≥ 11.0 kOe
Intrinsic Coercivity	Hcj	≥ 2786 kA/m	≥ 35.0 kOe
Maximum Energy Product	(BH) max	263-287 kJ/m <sup>3</sup>	33-36 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	$\partial$	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	$\beta$	-0.44 %/c	-0.40 %/c

