

N35SH



		SI	CGS
Remanence	Br	1.18-1.25 T	11.8-12.5 kG
Coercivity	Hcb	≥ 875 kA/m	≥ 11.0 kOe
Intrinsic Coercivity	Hcj	≥ 1592 kA/m	≥ 20.0 kOe
Maximum Energy Product	(BH) max	263-294 kJ/m ³	33-37 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.61 %/c	-0.55 %/c

