

N35UH



		SI	CGS
Remanence	Br	1.18-1.25 T	11.8-12.5 kG
Coercivity	Hcb	≥ 892 kA/m	≥ 11.2 kOe
Intrinsic Coercivity	Hcj	≥ 1990 kA/m	≥ 25.0 kOe
Maximum Energy Product	(BH) max	263-295 kJ/m ³	33-37 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	∂	-0.10 %/c	-0.11 %/c
Temperature Coefficient of Hcj	β	-0.57 %/c	-0.51 %/c

