

N38EHS



		SI	CGS
Remanence	Br	1.22-1.27 T	12.2-12.7 kG
Coercivity	Hcb	≥ 923 kA/m	≥ 11.6 kOe
Intrinsic Coercivity	Hcj	≥ 2627 kA/m	≥ 33.0 kOe
Maximum Energy Product	(BH) max	287-310 kJ/m ³	36-39 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.44 %/c	-0.40 %/c

