

N38H



		SI	CGS
Remanence	Br	1.23-1.30 T	12.3-13.0 kG
Coercivity	Hcb	≥ 915 kA/m	≥ 11.5 kOe
Intrinsic Coercivity	Hcj	≥ 1353 kA/m	≥ 17.0 kOe
Maximum Energy Product	(BH) max	287-318 kJ/m ³	36-40 MGOe

20-100°C		
Temperature Coefficient of Br	∂	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.65 %/c

