

# N40EH



		SI	CGS
Remanence	Br	1.26-1.32 T	12.6-13.2 kG
Coercivity	Hcb	≥ 939 kA/m	≥ 11.8 kOe
Intrinsic Coercivity	Hcj	≥ 2229 kA/m	≥ 28.0 kOe
Maximum Energy Product	(BH) max	302-326 kJ/m <sup>3</sup>	38-41 MGOe
		20-140°C	20-180°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.47 %/c	-0.44 %/c

