

N44H



		SI	CGS
Remanence	Br	1.30-1.37 T	13.0-13.7 kG
Coercivity	Hcb	≥ 963 kA/m	≥ 12.10 kOe
Intrinsic Coercivity	Hcj	≥ 1353 kA/m	≥ 17.0 kOe
Maximum Energy Product	(BH) max	326-358 kJ/m ³	41-45 MGOe

20-100°C			
Temperature Coefficient of Br	∂		-0.12 %/c
Temperature Coefficient of Hcj	β		-0.65 %/c

