

N48SH



		SI	CGS
Remanence	Br	1.36-1.42 T	13.6-14.2 kG
Coercivity	Hcb	≥ 1011 kA/m	≥ 12.7 kOe
Intrinsic Coercivity	Hcj	≥ 1512 kA/m	≥ 19.0 kOe
Maximum Energy Product	(BH) max	358-390 kJ/m ³	45-49 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.61 %/c	-0.55 %/c

